

Class 155 Polyurethane with Self-Bonding Overcoat Round Copper Magnet Wire for Solderable Applications

Table1 Specifications

	,				
Insulation materials	The conductor shall be coated with a				
	dual film.				
	The underlying coating is based on				
	polyurethane resins.				
	The superimposed coating is based on				
	resins that are self-bonding in character.				
Dimensions	Type 1: 25-52 AWG in accordance with				
	0.0292mm-0.516mm				
	Type 2: 25-50 AWG in accordance with				
	0.0406mm-0.538mm				
Certificate	MW 131-C				
Thermal Class	155				




Table 2 Periodic conformance tests

Thermoplastic Flow	Median not less than 200°C
Dielectric breakdown at	Average not less than 75% of the value required at room temperature
rated temperature	
Bond strength at elevated	Bond conditions and strength requirements as agreed between customer
temperature	and supplier



Table 3 Properties

Adherence and flexibility	No cracks visible in the film coating					
Elongation	Not less than the value in 5-38					
Heat shock	No cracks visible in the film coating after conditioning at 175°C					
Springback	Not greater than the value in Type 1 42-66; Type 2 46-70					
Dielectric breakdown	25-37 AWG: not less than the value in					
	Type 1 1360v-2640v; Type 2 2270v-4740v					
	38-52 AWG: not less than the value in Type 1 120v-500v; Type 2 250v-950v					
Continuity	25-44 AWG: max number of discontinuities in accordance with Type 1					
	350-1000; Type 2 500-1500 45-52 AWG: max number of discontinuities in accordance with Type 1 25; Type 2 10					
Solderability	Covered with continuous film of solder after immersion within the time and					
	temperature specified:					
	AWG Size	Temperature	Type 1	Type 2		
	25-29.5	390°C	5 seconds	6 seconds		
	30-36	390°C	4 seconds	5 seconds		
	37-46	390°C	3 seconds	4 seconds		
	47-56	360°C	2 seconds	3 seconds		



郑州蓝普实业有限公司

Zhengzhou LP Industry CO., LTD.

Phone: 0086-19337889070

Web: https://lpwindingwire.com

Email: office@cnlpzz.com

Add: NO. 86 Jingsan Road, Jinshui District, Zhengzhou, China